

## Graphic Vapour

<b>Tuft gauge</b>	1/10 loop pile	ISO 2424
<b>Pilecomposition</b>	100% PA SDN	ISO 2424
<b>Primary Backing</b>	Non Woven	ISO 2424
<b>Secondary backing</b>	Bitumen	ISO 2424
<b>Width</b>	50x50 cm ± 0,2%	EN 984
<b>Pile Density</b>	0,111 gr/cm <sup>3</sup>	ISO 8543
<b>Pile Weight</b>	795 gr/m <sup>2</sup>	ISO 8543
<b>Total weight</b>	Bitumen : 4550 gr/m <sup>2</sup> ± 15%	ISO 8543
<b>Pile height</b>	3 mm ± 2 mm	ISO 1766
<b>Total Height</b>	Bitumen : 7 mm	ISO 1765
<b>Number of knots</b>	239.792 /m <sup>2</sup> -7.5% .+10%	ISO 1763
<b>Fire Classification</b>	Bfl-S1	EN 13501-1
<b>Transversal resistance</b>	Ω	ISO 10965
<b>Use Area</b>	Heavy project use (33)	EN 1307
<b>Sound Absorption</b>	125 Hz 250 Hz 500 Hz 1000 Hz 2000 Hz 4000 Hz 0,00 0,00 0,05 0,20 0,25 0,25	ISO 11654
<b>Evaluated sound absorptions grade</b>	0,15 αW αW	ISO 11654
<b>Sound Insulation</b>	25 dB	ISO 10140
<b>Thermal resistance</b>	ca. 0.07 (0.7 TOG) M <sup>2</sup> KW	ISO 8302
<b>Light fastness</b>	≥ 5	105-B02
<b>Wearebility</b>	≥ 4	105-X12
<b>Water fastness</b>	≥ 4	105-E01
<b>Electrostatic charging</b>	<2 kV	ISO 6356
<b>Luxury class</b>	LC3	EN 1307
<b>Pictures</b>	www.condorcontract.com	

## Floorsymbols



## Certificates



2018

Condor Carpets  
Euroweg 3  
8061 SB Hasselt  
EN1307

DOP: C-003RBV269

Reaction to fire:  
Bfl-s1

Slip resistance: DS

Resilient floor  
covering to be  
used within a  
building

